

No. : CE/2016/25399

Date : 2016/03/07

Page: 1 of 7

CHUNG TAI SING CHEMICAL INDUSTRY CO., LTD. 105 NIU PU SOUTH ROAD, HSINCHU, TAIWAN, R. O. C.

The following sample(s) was/were submitted and identified by/on behalf of the applicant as :

Sample Submitted By	:	CHUNG TAI SING CHEMICAL INDUSTRY CO., LTD.
Sample Description	:	PUFF DINO SPRAY PAINT
Style/Item No.	:	PP109A
Sample Receiving Date	:	2016/02/26
Testing Period	:	2016/02/26 TO 2016/03/07

Test Requested

 As specified by client, with reference to RoHS 2011/65/EU Annex II and amending Directive (EU) 2015/863 to determine Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, BBP, DEHP, DIBP contents in the submitted sample.

(2) Please refer to next pages for the other item(s).

Test Result(s) : Please refer to next page(s).





No. : CE/2016/25399

Date : 2016/03/07

Page : 2 of 7

CHUNG TAI SING CHEMICAL INDUSTRY CO., LTD. 105 NIU PU SOUTH ROAD, HSINCHU, TAIWAN, R. O. C.

Test Result(s)

PART NAME No.1 : BLACK LIQUID

Test Item(s)	Unit	Method	MDL	Result
				No.1
Cadmium (Cd)	mg/kg	With reference to IEC 62321-5: 2013 and performed by ICP-AES.	2	n.d.
Lead (Pb)	mg/kg	With reference to IEC 62321-5: 2013 and performed by ICP-AES.	2	n.d.
Mercury (Hg)	mg/kg	With reference to IEC 62321-4: 2013 and performed by ICP-AES.	2	n.d.
Hexavalent Chromium Cr(VI)	mg/kg	With reference to IEC 62321: 2008 and performed by UV-VIS.	2	n.d.
Sum of PBBs	mg/kg		-	n.d.
Monobromobiphenyl	mg/kg		5	n.d.
Dibromobiphenyl	mg/kg		5	n.d.
Tribromobiphenyl	mg/kg	1	5	n.d.
Tetrabromobiphenyl	mg/kg	1 1	5	n.d.
Pentabromobiphenyl	mg/kg	1	5	n.d.
Hexabromobiphenyl	mg/kg	1	5	n.d.
Heptabromobiphenyl	mg/kg	With reference to IEC 62321-6: 2015 and performed by GC/MS.	5	n.d.
Octabromobiphenyl	mg/kg		5	n.d.
Nonabromobiphenyl	mg/kg		5	n.d.
Decabromobiphenyl	mg/kg		5	n.d.
Sum of PBDEs	mg/kg		-	n.d.
Monobromodiphenyl ether	mg/kg] [5	n.d.
Dibromodiphenyl ether	mg/kg		5	n.d.
Tribromodiphenyl ether	mg/kg		5	n.d.
Tetrabromodiphenyl ether	mg/kg		5	n.d.
Pentabromodiphenyl ether	mg/kg		5	n.d.
Hexabromodiphenyl ether	mg/kg		5	n.d.
Heptabromodiphenyl ether	mg/kg		5	n.d.
Octabromodiphenyl ether	mg/kg		5	n.d.
Nonabromodiphenyl ether	mg/kg		5	n.d.
Decabromodiphenyl ether	mg/kg		5	n.d.



No.: CE/2016/25399

Date : 2016/03/07

Page : 3 of 7

CHUNG TAI SING CHEMICAL INDUSTRY CO., LTD. 105 NIU PU SOUTH ROAD, HSINCHU, TAIWAN, R. O. C.

Test Item(s)	Unit	Method	MDL	Result
				No.1
BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7)	mg/kg	With reference to IEC 62321-8 (111/321/CD). Analysis was performed by GC/MS.	50	n.d.
DBP (Dibutyl phthalate) (CAS No.: 84-74-2)	mg/kg	With reference to IEC 62321-8 (111/321/CD). Analysis was performed by GC/MS.	50	n.d.
DEHP (Di- (2-ethylhexyl) phthalate) (CAS No.: 117-81-7)	mg/kg	With reference to IEC 62321-8 (111/321/CD). Analysis was performed by GC/MS.	50	n.d.
DIBP (Di-isobutyl phthalate) (CAS No.: 84-69-5)	mg/kg	With reference to IEC 62321-8 (111/321/CD). Analysis was performed by GC/MS.	50	n.d.
DIDP (Di-isodecyl phthalate) (CAS No.: 26761-40-0; 68515-49-1)	mg/kg	With reference to IEC 62321-8 (111/321/CD). Analysis was performed by GC/MS.	50	n.d.
DINP (Di-isononyl phthalate) (CAS No.: 28553-12-0; 68515-48-0)	mg/kg	With reference to IEC 62321-8 (111/321/CD). Analysis was performed by GC/MS.	50	n.d.
DNOP (Di-n-octyl phthalate) (CAS No.: 117-84-0)	mg/kg	With reference to IEC 62321-8 (111/321/CD). Analysis was performed by GC/MS.	50	n.d.

Note :

- 1. mg/kg = ppm ; 0.1wt% = 1000ppm
- 2. n.d. = Not Detected
- 3. MDL = Method Detection Limit
- 4. " " = Not Regulated



No. : CE/2016/25399

Date : 2016/03/07

Page: 4 of 7

CHUNG TAI SING CHEMICAL INDUSTRY CO., LTD. 105 NIU PU SOUTH ROAD, HSINCHU, TAIWAN, R. O. C.

These samples were dissolved totally by pre-conditioning method according to below flow chart. (Cr^{6+} test method excluded)

Technician: Climbgreat Yang Supervisor: Troy Chang Cutting / Preparation Sample Measurement Cr⁶⁺ Hg Pb、Cd (Note**) Acid digestion by suitable acid Microwave digestion with Add appropriate amount HNO₃/HCI/HF depended on different sample of digestion reagent material (as below table) Heat to appropriate Filtration temperature to extract Residue Solution Cool, filter digestate through filter 1) Alkali Fusion 2) HCl to dissolve **ICP-AES** Add diphenyl-carbazide for color development **Digestion Acid** Sample Material Steel, copper, aluminum, solder Aqua regia, HNO₃, HCI, HF, H₂O₂ Glass HNO₃/HF measure the absorbance Gold, platinum, palladium, ceramic Aqua regia at 540 nm by UV-VIS HNO₃ Silver Plastic H₂SO₄, H₂O₂, HNO₃, HCI Added appropriate reagent to total Others digestion

Note** (For IEC 62321)

(1) For non-metallic material, add alkaline digestion reagent and heat to $90~95^{\circ}$ C.

(2) For metallic material, add pure water and heat to boiling.




No. : CE/2016/25399

Date : 2016/03/07

Page : 5 of 7

CHUNG TAI SING CHEMICAL INDUSTRY CO., LTD. 105 NIU PU SOUTH ROAD, HSINCHU, TAIWAN, R. O. C.

Analytical flow chart - PBB/PBDE



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-an



No. : CE/2016/25399

Date : 2016/03/07


Page : 6 of 7

CHUNG TAI SING CHEMICAL INDUSTRY CO., LTD. 105 NIU PU SOUTH ROAD, HSINCHU, TAIWAN, R. O. C.

Analytical flow chart - Phthalate

- Technician: Andy Shu
- Supervisor: Troy Chang

[Test method: IEC 62321-8]





No. : CE/2016/25399

Date : 2016/03/07

Page : 7 of 7

CHUNG TAI SING CHEMICAL INDUSTRY CO., LTD. 105 NIU PU SOUTH ROAD, HSINCHU, TAIWAN, R. O. C.

* The tested sample / part is marked by an arrow if it's shown on the photo. *



** End of Report **