

TEST REPORT

Report No. : HV-08-01637X

Page : 1 of 3

Date : MAY 05 , 2008

Chung Tai Sing Chemical Industry Co.,Ltd.

105 Niu Pu South Road, Hsinchu, Taiwan, R.O.C

The following merchandise was submitted and identified by the vendor as:

Type of Product : Puff Dino Long-Term Effect Anti-Rust Spray

Style/Item No. : DI70

Buyer/Order No : CHUNG TAI SING CHEMICAL INDUSTRY CO.,LTD.

Country of Origin : Taiwan

We have tested the submitted sample(s) as requested and the following results were obtained :

Test Required : (According to client's test specification, please see following sheets in detail.)


Salt Spray Test

Test Result :

- PLEASE SEE ATTACHED SHEETS -

Date of Testing : APRIL 21, 2007~APRIL 30, 2008

Signed for and on behalf of
SGS Taiwan Ltd.



Given Chang
Asst. Manager

TEST REPORT

Report No. : HV-08-01637X

Page : 2 of 3

Date : MAY 05 , 2008

Salt Spray Test

Test Equipment:

Name	Brand	Model
Salt Spray Test Chamber	CHUN YEN	Salt Spray

Lab Environmental Conditions:

Ambient Temperature : $23 \pm 2^{\circ}\text{C}$

Relative humidity: $50 \pm 5\% \text{RH}$

Test Method/ Specification:

ASTM B117-03 Standard Practice for Operating Salt Spray (Fog) Apparatus

Salt solution: 5 wt.% NaCl solution

pH of solution: 6.5-7.2

Temperature: $35 \left(\begin{smallmatrix} +1.1 \\ -1.7 \end{smallmatrix} \right)^{\circ}\text{C}$

Quantity of fog : 1.0 ~2.0 ml/ 80 cm²/ hour

Exposing duration: 120 hrs

ASTM B537-70(2002) Standard Practice for Rating of Electroplated Panels

Subjected to Atmospheric Exposure

※ Examine the appearance of specimen(s) by visual check

Test Result:

5 (1.0 to 2.5 % Area of Defect)

TEST REPORT

Report No. : HV-08-01637X

Page : 3 of 3

Date : MAY 05 , 2008

Test Photo :

	
<p>Puff Dino Long-Term Effect Anti-Rust Spray</p>	<p>Before Salt Spray test</p>
	<p>-</p>
<p>After Salt Spray Test</p>	<p>-</p>

— The End of Test Report —